



جدول مشخصات لوله‌های U-PVC پارس اتیلن کیش

U-PVC Pipe Chart

Size	Thickness	Outside Diameter	Weight	Specifications	Tolerance Pressure
inches	mm	mm	Kg	Pressure Tolerance	Atmosphere
1/2	2,3	20	1	Strong Pressure	20
3/4	1,5	25	1	Sewage System	10
	1,9	25	1.2	Pressure in half	16
	2,8	25	1.7	Strong Pressure	20
1	1,8	32	1.5	Sewage System	10
	2,4	32	1.9	Pressure in half	16
	3,6	32	2.7	Strong Pressure	20
1.1/4	1,8	40	1.9	Sewage System	6
	3	40	2.9	Pressure in half	10
	4,5	40	4.2	Strong Pressure	16
1.1/2	1,8	50	2.4	Sewage System	6
	2,4	50	3.1	Pressure in half	10
	3,7	50	4.5	Strong Pressure	16
	5,6	50	6.4	Ultra Strong Pressure	20
2	1,9	63	3.1	Sewage System	6
	3	63	4.8	Pressure in half	10
	4,7	63	7.2	Strong Pressure	16
	7	63	10	Ultra Strong Pressure	20
2.1/2	1,8	75	3.6	Sewage System	4
	2,2	75	4.4	Pressure in half	6
	3,6	75	6.8	Strong Pressure	10
3	1,8	90	4.3	Sewage System	4
	2,7	90	6.3	Pressure in half	6
	4,3	90	9.7	Strong Pressure	10
	6,7	90	14.4	Ultra Strong Pressure	16

Office Address

No. 18, Mina Blvd.,
Africa St., Tehran/Iran

Tel: (+98 - 21) 88 20 20 60 (50 Line)

Fax: (+98 - 21) 88 20 20 81

info@parsethylene-kish.com

www.parsethylene-kish.com

دفتر مرکزی

تهران، خیابان آفریقا،

بلوار مینا، پلاک ۱۸

تلفن : (۵۰ خط) ۲۰ ۲۰ ۸۸

فکس : ۲۰ ۸۱ ۸۸

جدول مشخصات لوله‌های U-PVC پارس اتیلن کیش

U-PVC Pipe Chart

4	2,2	110	6.4	Sewage System	4
	3,2	110	9.1	Pressure in half	6
	5,3	110	14.4	Strong Pressure	10
	8,2	110	21.5	Ultra Strong Pressure	16
5	2,5	125	8.2	Sewage System	4
	3,7	125	11.8	Pressure in half	6
	6	125	18.5	Strong Pressure	10
	9,3	125	27.8	Ultra Strong Pressure	16
6	3,2	160	13.3	Sewage System	4
	4,7	160	19	Pressure in half	6
	7,7	160	30.2	Strong Pressure	10
	11,9	160	45.1	Ultra Strong Pressure	16
8	4	200	20.5	Sewage System	4
	5,9	200	29.7	Pressure in half	6
	9,6	200	47	Strong Pressure	10
10	4,9	250	31.2	Sewage System	4
	7,3	250	45.9	Pressure in half	6
	11,9	250	72.9	Strong Pressure	10
12	6,2	315	49.8	Sewage System	4
	9,2	315	72.9	Pressure in half	6
	15	315	115.4	Strong Pressure	10
16	7,9	400	80	Sewage System	4
	11,7	400	116.5	Pressure in half	6
	19,1	400	186	Strong Pressure	10

Office Address

No. 18, Mina Blvd.,
Africa St., Tehran/Iran

Tel: (+98 - 21) 88 20 20 60 (50 Line)

Fax: (+98 - 21) 88 20 20 81

info@parsethylene-kish.com

www.parsethylene-kish.com

دفتر مرکزی

تهران، خیابان آفریقا،

بلوار مینا، پلاک ۱۸

تلفن: (۵۰ خط) ۸۸ ۲۰ ۲۰ ۶۰

فکس: ۸۸ ۲۰ ۲۰ ۸۱