



DPC: 08/30191156 DC

Head Office389 Chiswick High Road
London W4 4AL

Telephone: +44(0)20 8996 9000

Fax: +44(0)20 8996 7001

Date: 18 December 2008

Origin: European

Latest date for receipt of comments: 31 March 2009

Project no.: 2008/03316

Responsible committee: PRI/88/2 Plastics piping for pressure applications

Interested committees:

Title: Draft BS EN 1555-5 Plastics piping systems for the supply of gaseous fuels - Polyethylene (PE)
Part 5: Fitness for purpose of the system

Supersession information: If this document is published as a standard, the UK implementation of it will supersede BSEN1555-5 : 2002 and partially supersede. NONE If you are aware of a current national standard which may be affected, please notify the secretary (contact details below).

**WARNING: THIS IS A DRAFT AND MUST NOT BE REGARDED OR USED AS A BRITISH STANDARD.
THIS DRAFT IS NOT CURRENT BEYOND 31 March 2009.**

This draft is issued to allow comments from interested parties; all comments will be given consideration prior to publication. No acknowledgement will normally be sent. **See overleaf for information on commenting.**

No copying is allowed, in any form, without prior written permission from BSI except as permitted under the Copyright, Designs and Patent Act 1988 or for circulation within a nominating organization for briefing purposes. Electronic circulation is limited to dissemination by e-mail within such an organization by committee members.

Further copies of this draft may be purchased from BSI Customer Services, Tel: +44(0) 20 8996 9001 or email cservices@bsigroup.com. British, International and foreign standards are also available from BSI Customer Services.

Information on the co-operating organizations represented on the committees referenced above may be obtained from the responsible committee secretary.

Cross-references

The British Standards which implement International or European publications referred to in this draft may be found via the British Standards Online Service on the BSI web site <http://www.bsigroup.com>.

Responsible Committee Secretary: Committee Service
Centre (BSI)

Direct tel: 020 8996 7009

E-mail: csc@bsigroup.com

Introduction

This draft standard is based on European discussions in which the UK has taken an active part. Your comments on this draft are welcome and will assist in the preparation of the consequent British Standard. Comment is particularly welcome on national, legislative or similar deviations that may be necessary.

Even if this draft standard is not approved by the UK, if it receives the necessary support in Europe, the UK will be obliged to publish the official English Language text unchanged as a British Standard and to withdraw any conflicting standard.

UK Vote

Please indicate whether you consider the UK should submit a negative (with reasons) or positive vote on this draft.

Submission

The guidance given below is intended to ensure that all comments receive efficient and appropriate attention by the responsible BSI committee. **Annotated drafts are not acceptable and will be rejected.**

All comments must be submitted, preferably electronically, to the Responsible Committee Secretary at the address given on the front cover. Comments should be compatible with Version 6.0 or Version 97 of Microsoft® Word for Windows™, if possible; otherwise comments in ASCII text format are acceptable. **Any comments not submitted electronically should still adhere to these format requirements.**

All comments submitted should be presented as given in the example below. Further information on submitting comments and how to obtain a blank electronic version of a comment form are available from the BSI web site at: <http://www.bsigroup.com/en/Standards-and-Publications/Current-work/DPCs/>

Template for comments and secretariat observations

Date: xx/xx/200x

Document: **ISO/DIS xxxxx**

1	2	(3)	4	5	(6)	(7)
MB	Clause No./ Subclause No./ Annex (e.g. 3.1)	Paragraph/ Figure/Table/ Note (e.g. Table 1)	Type of comment	Comment (justification for change) by the MB	Proposed change by the MB	Secretariat observations on each comment submitted
	3.1	Definition 1	ed	Definition is ambiguous and needs clarifying.	Amend to read '... so that the mains connector to which no connection ...'	
	6.4	Paragraph 2	te	The use of the UV photometer as an alternative cannot be supported as serious problems have been encountered in its use in the UK.	Delete reference to UV photometer.	

Microsoft and MS-DOS are registered trademarks, and Windows is a trademark of Microsoft Corporation.

December 2008

ICS 23.040.01; 91.140.40

Will supersede EN 1555-5:2002

English Version

Plastics piping systems for the supply of gaseous fuels - Polyethylene (PE) - Part 5: Fitness for purpose of the system

Systèmes de canalisations en plastique pour la distribution
de combustibles gazeux - Polyéthylène (PE) - Partie 5:
Aptitude à l'emploi du système

Kunststoff-Rohrleitungssysteme für die Gasversorgung -
Polyethylen (PE) - Teil 5: Gebrauchstauglichkeit des
systems

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 155.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	6
4 Fitness for purpose	6
4.1 Method of preparation of assemblies for testing	6
4.1.1 General	6
4.1.2 Butt fusion joints	7
4.1.3 Electrofusion jointing	7
4.1.4 Mechanical joints	7
4.2 Requirements for fitness for purpose	7
4.2.1 Fitness for purpose for butt fusion joints	7
4.2.2 Fitness for purpose for electrofusion joints	8
4.2.3 Fitness for purpose for mechanical joints	10
5 Overall service (design) coefficient	11
Annex A (informative) Derating coefficients for operating temperatures	12
Annex B (informative) Rapid crack propagation (RCP) resistance at temperature less than 0 °C	13
Bibliography	14

www.parseethylene-kish.com

Foreword

This document (prEN 1555-5:2008) has been prepared by Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems", the secretariat of which is held by NEN.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 1555-5:2002.

It has been prepared in liaison with Technical Committee CEN/TC 234 "Gas supply".

This standard is a part of a System Standard for plastics piping systems of a particular material for a specified application. There are a number of such System Standards.

System Standards are based on the results of the work undertaken in ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids", which is a Technical Committee of the International Organization for Standardization (ISO).

They are supported by separate standards on test methods to which references are made throughout the System Standard.

The System Standards are consistent with general standards on functional requirements and on recommended practice for installation.

EN 1555 consists of the following parts, under the general title *Plastics piping systems for the supply of gaseous fuels - Polyethylene (PE)*:

- *Part 1: General*
- *Part 2: Pipes*
- *Part 3: Fittings*
- *Part 4: Valves*
- *Part 5: Fitness for purpose of the system* (this standard)
- *Part 7: Guidance for assessment of conformity* (CEN /TS).

NOTE The document dealing with recommended practice for installation which was initially submitted for CEN enquiry as prEN 1555-6 [1] was withdrawn when EN 12007-2 [2], prepared by CEN /TC 234 Gas supply, was published with the title *Gas supply systems — Pipelines for maximum operating pressure up to and including 16 bar — Part 2: Specific functional recommendations for polyethylene (MOP up to and including 10 bar)*".

Introduction

The System Standard, of which this is Part 5, specifies the requirements of a piping system and its components made from polyethylene (PE) and which is intended to be used for the supply of gaseous fuels.

Requirements and test methods for material and components are specified in prEN 1555-1:2008, prEN 1555-2:2008, prEN 1555-3:2008 and prEN 1555-4:2008. CEN /TS 1555-7 gives guidance for assessment of conformity. Recommended practice for installation is given in EN 12007-2 [2] prepared by CEN /TC 234.

This part of EN 1555 covers the characteristics of fitness for purpose of the system.

www.parsethylene-kish.com

1 Scope

This part of EN 1555 specifies requirements of fitness for purpose of the polyethylene (PE) piping system in the field of the supply of gaseous fuels.

It specifies the definitions of electrofusion, butt fusion and mechanical joints.

It also specifies the method of preparation of test piece joints, and the tests to be carried out on these joints for assessing the fitness for purpose of the system under normal and extreme conditions.

It also specifies the test parameters for the test methods referred to in this standard.

In conjunction with the other parts of EN 1555 (see Foreword) it is applicable to PE pipes, fittings, valves, their joints and to joints with components of other materials intended to be used under the following conditions:

- a) a maximum operating pressure, MOP, up to and including 10 bar ¹⁾;
- b) an operating temperature of 20 °C as reference temperature.

NOTE 1 For other operating temperatures, derating coefficients should be used, see Annex A.

EN 1555 covers a range of maximum operating pressures and gives requirements concerning colours and additives.

NOTE 2 It is the responsibility of the purchaser or specifier to make the appropriate selections from these aspects, taking into account their particular requirements and any relevant national regulations and installation practices or codes.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

prEN 1555-1:2008, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 1: General*.

EN ISO 1167-1:2006, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method (ISO 1167-1:2006)*

EN ISO 1167-2, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 2: Preparation of pipe test pieces (ISO 1167-2:2006)*

EN ISO 1167-3, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 3: Preparation of components (ISO 1167-3:2007)*

EN ISO 1167-4, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 4: Preparation of assemblies (ISO 1167-4:2007)*

EN ISO 13477, *Thermoplastics pipes for the conveyance of fluids — Determination of resistance to rapid crack propagation (RCP) — Small-scale-steady-state test (S4 test) (ISO 13477:2008)*.

EN ISO 13478, *Thermoplastics pipes for the conveyance of fluids — Determination of resistance to rapid crack propagation (RCP) — Full scale test (FST) (ISO 13478:2007)*.

ISO 10838-1 ²⁾, *Mechanical fittings for polyethylene piping systems for the supply of gaseous fuels — Part 1: Metal fittings for pipes of nominal outside diameter less than or equal to 63 mm*.

1) 1 bar = 0,1 MPa

2) These standards are under revision.

ISO 10838-2²⁾, *Mechanical fittings for polyethylene piping systems for the supply of gaseous fuels — Part 2: Metal fittings for pipes of nominal outside diameter greater than 63 mm.*

ISO 10838-3²⁾, *Mechanical fittings for polyethylene piping systems for the supply of gaseous fuels — Part 3: Thermoplastics fittings for pipes of nominal outside diameter less than or equal to 63 mm.*

ISO/FDIS 11413, *Plastics pipes and fittings — Preparation of test piece assemblies between a polyethylene (PE) pipe and an electrofusion fitting.*

ISO/FDIS 11414:2008, *Plastics pipes and fittings — Preparation of polyethylene (PE) pipe/pipe or pipe/fitting test assemblies by butt fusion.*

ISO 13953, *Polyethylene (PE) pipes and fittings — Determination of the tensile strength and failure mode of test pieces from a butt-fused joint.*

ISO 13954, *Plastics pipes and fittings — Peel decohesion test for polyethylene (PE) electrofusion assemblies of nominal outside diameter greater than or equal to 90 mm.*

ISO 13955, *Plastics pipes and fittings — Crushing decohesion test for polyethylene (PE) electrofusion assemblies.*

ISO/CD 13956, *Plastics pipes and fittings — Determination of cohesive strength — Tear test for polyethylene (PE) assemblies.*

3 Terms and definitions

For the purposes of this European Standard, the terms and definitions, symbols and abbreviations given in prEN 1555-1:2008 apply, together with the following.

3.1

electrofusion joint

joint between a PE electrofusion socket or saddle fitting and a pipe or a spigot end fitting

NOTE The electrofusion fittings are heated by the Joule effect of the heating element incorporated at their jointing surfaces, causing the material adjacent to them to melt and the pipe and fitting surfaces to fuse.

3.2

mechanical joint

joint made by assembling a PE pipe with a fitting that generally includes a compression part to provide for pressure integrity, leaktightness and resistance to end loads.

NOTE A support sleeve inserted into the pipe bore should be used to provide a permanent support for the PE pipe to prevent creep in the pipe wall under radial compressive forces. The metallic part of this fitting can be assembled to a metallic pipe by screw threads, compression joints, welded or brazed flanges or by other means.

4 Fitness for purpose

4.1 Method of preparation of assemblies for testing

4.1.1 General

The joints shall be made by using pipes conforming to prEN 1555-2:2008, fittings conforming to prEN 1555-3:2008 or valves conforming to prEN 1555-4:2008.

Test pieces for pressure test shall be closed with pressure-tight, end-load-bearing end caps, plugs or flanges which shall be provided with connections for the entry of water and release of air.

4.1.2 Butt fusion joints

PE pipes, spigot end fittings and valves intended to be used for jointing by butt fusion shall be prepared and assembled in accordance with ISO/FDIS 11414: 2008. The conditions for the preparation of the joints are given in 4.2.1.1 for the assessment of fitness for purpose under normal conditions and in 4.2.1.2 for the assessment of fitness for purpose under extreme conditions.

4.1.3 Electrofusion jointing

PE pipes, fittings and valves intended to be used for jointing by electrofusion shall be prepared and assembled in accordance with ISO/FDIS 11413. The conditions for the preparation of the joints are given in 4.2.2.1 for the assessment of fitness for purpose under normal conditions and in 4.2.2.2 for the assessment of fitness for purpose under extreme conditions.

For joints with electrofusion socket fittings and joints with electrofusion saddle fittings, test joints shall be prepared to check the fitness for purpose of the fittings under extreme jointing conditions.

For joints with electrofusion saddle fittings, the electrofusion saddle fitting shall be fused to the pipe, while it is pneumatically pressurized to the allowable maximum operating pressure. The pipe shall be cut immediately after the manufacturer prescribed cooling time has elapsed.

NOTE These joints with electrofusion saddle fitting should be prepared taking into consideration national safety regulations.

For straight equal electrofusion socket fittings (couplers) test joints on selected diameters out of the product range shall be prepared with a gap of $0,05d_n$ between the pipe end and the maximum theoretical depth of penetration of the fitting, where for diameters greater than 225 mm the adjoining pipes shall be arranged to provide the maximum angular deflection possible for the fitting, limited to 1,5.

4.1.4 Mechanical joints

For mechanical joints the assembly of the PE pipe and the fitting shall be prepared in accordance with ISO 10838-1, ISO 10838-2 or ISO 10838-3, as applicable.

4.2 Requirements for fitness for purpose

4.2.1 Fitness for purpose for butt fusion joints

4.2.1.1 Under normal conditions (ambient temperature 23 °C)

For the assessment of fitness for purpose under normal conditions, butt fusion joints shall have the characteristic of tensile strength conforming to the requirement given in Table 5, using the parameters as specified in Annex B Condition 1 of ISO/FDIS 11414:2008 at an ambient temperature of (23 ± 2) °C and the scheme listed in Table 1.

Table 1 — Scheme for butt-fused joints

Pipe/spigot end fitting/valve with spigot ends	Pipe	
	PE 80	PE 100
PE 80	X	X ^a
PE 100	X ^a	X
^a Only when requested by the purchaser.		

NOTE The table should be interpreted as follows: as an example, for a pipe or a spigot end fitting or a valve with spigot end made from a PE 80 compound, a joint should be tested with a pipe made from PE 80 compound. When requested by the purchaser, for mixed compound joints, test pieces should be used incorporating PE 80 and PE 100 compounds.

The pipe manufacturer shall declare, according to 4.2.1.1, which pipes from his own product range conforming to prEN 1555-2:2008 are compatible to each other for butt fusion.

The fitting or valve manufacturer shall declare, according to 4.2.1.1 the SDR range and MRS values of pipes conforming to prEN 1555-2:2008 to which his fittings conforming to prEN 1555-3:2008 or and his valves conforming to prEN 1555-4:2008 can be fused by using the same procedures (e.g. times, temperatures, fusion pressures) to conform to this standard. If there is a need for deviation in fusion procedures the fitting or valve manufacturer shall state this clearly.

4.2.1.2 Under extreme conditions

For butt fusion joints the characteristics to be examined for fitness for purpose under extreme conditions shall conform to Table 2.

Table 2 — Relation between the joints and fitness for purpose characteristics

Butt fusion joint (C)	Associated characteristics
Both components of the joint: same MRS and same SDR Joint: minimum and maximum condition ^a	Hydrostatic strength (80 °C, 165 h)
Both components of the joint: same MRS and same SDR Joint: minimum and maximum condition ^a	Tensile strength for butt fusion joint
^a As specified in Clause 7, item a), of ISO/FDIS 11414:2008 concerning misalignment and the limit values of fusion parameters conforming to Condition 1 in Annex B of ISO/FDIS 11414:2008.	

When tested in accordance with the test methods as specified in Table 5 using the indicated parameters, the joints shall have characteristics conforming to the requirements given in Table 5.

The fitting or valve manufacturer shall declare according to Table 2, as applicable, the fitness for purpose under extreme conditions of his fittings or valves.

The pipe manufacturer shall declare according to Table 2 the fitness for purpose under extreme conditions of his pipes.

4.2.2 Fitness for purpose for electrofusion joints

4.2.2.1 Under normal conditions (ambient temperature 23 °C)

For the assessment of fitness for purpose under normal conditions, electrofusion joints shall have the characteristic of decohesive resistance or cohesive strength, as applicable, conforming to the requirement given in Table 5, using the assembly condition 1 as specified in Annex C of ISO/FDIS 11413 at an ambient temperature of (23 ± 2) °C and the scheme listed in Table 3.

Table 3 — Scheme for electrofused joints

Electrofusion fitting/valve with electrofusion socket	Pipe	
	PE 80 SDR maximum	PE 100 SDR minimum
PE 80	X	X
PE 100	X	X

NOTE The table should be interpreted as follows: as an example, for an electrofusion fitting or a valve with electrofusion socket made from a PE 80 compound, a joint should be tested with a pipe made from PE 80 compound and the SDR maximum as declared by the manufacturer, and another joint should be tested with a pipe made from PE 100 compound and the SDR minimum as declared by the manufacturer.

The fitting or valve manufacturer shall declare, according to 4.2.2.1 the SDR range and MRS values of pipes conforming to prEN 1555-2:2008 to which his fittings conforming to prEN 1555-3:2008 or and his valves conforming to prEN 1555-4:2008 can be fused by using the same procedures (e.g. times, temperatures, fusion pressures) to conform to this standard. If there is a need for deviation in fusion procedures the fitting or valve manufacturer shall state this clearly.

4.2.2.2 Under extreme conditions

For electrofusion joints the characteristics to be examined for fitness for purpose under extreme conditions shall conform to Table 4.

When tested in accordance with the test methods as specified in Table 5 using the indicated parameters, the joints shall have characteristics conforming to the requirements given in Table 5.

Table 1 — Relation between the joints and fitness for purpose characteristics

Electrofusion joint including socket fitting ^a (A)	Electrofusion joint including saddle fitting ^a (B)	Associated characteristics
Pipe: MRS maximum ^b SDR minimum ^b Joint: conditions 2 and 3 ^c		Decohesive resistance
	Pipe: MRS maximum ^b SDR minimum ^b Joint: conditions 2 and 3 ^c	Cohesive strength
<p>a If accepted by the purchaser, the minimum and maximum energy conditions 2 and 3 may be replaced by a nominal energy at a given ambient temperature T_a defined by the fitting manufacturer (see 3.4 of ISO/FDIS 11413).</p> <p>b As declared by the fitting manufacturer according to 4.2.2.1.</p> <p>c As specified in Annex C of ISO/FDIS 11413 with T_{min} and T_{max} as stated in the fitting manufacturer's technical specification.</p>		

The fitting or valve manufacturer shall declare according to Table 4, column(s) A, or B, as applicable, the fitness for purpose under extreme conditions of his fittings or valves.

Table 5 — Characteristics for fitness for purpose of the system

Characteristic	Requirements	Test parameters		Test method
		Parameter	Value	
Hydrostatic strength (80 °C, 165 h) (c)	No failure during the test period ^a	End caps Orientation Conditioning time Number of test pieces ^b Type of test Circumferential (hoop) stress for: PE 80 PE 100 Test period Test temperature	EN ISO 1167-1:2006, Type a) Free Shall conform to EN ISO 1167-1:2006 3 Water-in water 4,5 MPa 5,4 MPa 165 h 80 °C	EN ISO 1167-1:2006 together with EN ISO 1167-2, or EN ISO 1167-3, or EN ISO 1167-4, as applicable
Decohesive resistance (a)	Length of initiation rupture $\leq L/3$ in brittle failure ^c	Test temperature Number of test pieces ^b	23 °C Shall conform to ISO 13954	ISO 13954
		Test temperature Number of test pieces ^b	23 °C Shall conform to ISO 13955	ISO 13955
Cohesive strength (b)	Surface of rupture $\leq 25\%$ brittle failure	Test temperature Number of test pieces ^b	23 °C Shall conform to ISO/CD 13956	ISO/CD 13956
Tensile strength for butt fusion (c)	Test to failure: ductile: pass brittle: fail	Test temperature Number of test pieces ^b	23 °C Shall conform to ISO 13953	ISO 13953

^a Only brittle failures shall be taken into account. If a ductile failure occurs before 165 h, the test is permitted to be repeated at a lower stress. The stress and the associated minimum test period shall be selected from Table 6 or from a line based on the stress/time points given in Table 6.

^b The numbers of test pieces given indicate the numbers required to establish a value for the characteristic described in the table. The numbers of test pieces required for factory production control and process control should be listed in the manufacturer's quality plan. For guidance see CEN/TS 1555-7 [2].

^c L is the nominal length of the fusion zone of the electrofusion socket fitting.

Table 6 — Circumferential (hoop) stress at 80 °C and associated minimum test period

PE 80		PE 100	
Stress MPa	Minimum test time h	Stress MPa	Minimum test time h
4,5	165	5,4	165
4,4	233	5,3	256
4,3	331	5,2	399
4,2	474	5,1	629
4,1	685	5,0	1000
4,0	1000	—	—

4.2.3 Fitness for purpose for mechanical joints

For fitness for purpose of mechanical joints the performances of the joints shall conform to ISO 10838-1, ISO 10838-2 or ISO 10838-3, as applicable.

5 Design coefficient

The minimum value of the design coefficient, C , for pipes, fittings and valves for the supply of gaseous fuels shall be 2, or higher values according to national legislation (see prEN 1555-1:2008).

To this value other coefficients may be applied taking into account different aspects such as:

- a) operating temperature range;
- b) specific material aspects, for instance Rapid Crack Propagation (RCP);

NOTE 1 For information about RCP resistance at temperature less than 0 °C, see Annex B.

- c) storage and laying conditions.

NOTE 2 For information about derating coefficients for other operating temperatures, see Annex A.

www.parsethylene-kish.com

Annex A (informative)

Derating coefficients for operating temperatures

Derating factor (D_F) is a coefficient used in the calculation of the maximum operating pressure (MOP), which takes into account the influence of operating temperature.

Table A.1 gives derating coefficients for various operating temperatures.

Table A.1 — Temperature derating coefficients

Temperature	Derating coefficient (D_F)
20 °C	1,0
30 °C	1,1
40 °C	1,3

For other temperatures between each step, linear interpolation is permitted.

The calculation of MOP for a given operating temperature is based on the following equation:

$$\text{MOP} = \frac{20 \times \text{MRS}}{(\text{SDR} - 1) \times C \times D_F},$$

in which the value of the design coefficient, C , shall not be less than 2 in accordance with Clause 5.

Annex B (normative)

Rapid crack propagation (RCP) resistance of pipe at temperature less than 0 °C for the distribution of LPG and use downstream of pressure reduction stations

Piping system intended for the distribution of gas at temperature less than 0 °C, e.g. liquid petroleum gas (LPG) systems and use downstream of pressure reduction stations, shall be subjected to additional rapid crack propagation (RCP) evaluation in accordance with EN ISO 13477 or EN ISO 13478, to determine the critical pressure p_c at the minimum expected operating temperature.

An additional marking “LPG” shall be applied (see EN 12007-2:2000 [2]).

www.parsethylene-kish.com

Bibliography

- [1] prEN 1555-6, *Plastics piping systems for gaseous fuels supply — Polyethylene (PE) — Part 6: Recommended practice for installation*
- [2] EN 12007-2:2000, *Gas supply systems — Pipelines for maximum operating pressure up to and including 16 bar — Part 2: Specific functional recommendations for polyethylene (MOP up to and including 10 bar)*.
- [3] CEN/TS 1555-7, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 7: Guidance for the assessment of conformity*.
- [4] prEN 1555-2:2008, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 2: Pipes*.
- [5] prEN 1555-3:2008, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 3: Fittings*.
- [6] prEN 1555-4:2008, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 4: Valves*.

www.parsethylene.kish.com