

**Aerospace series —  
Steel FE-PM1505  
(X1CrNiMoAlTi12-9-2) —  
Vacuum induction  
melted and consumable  
electrode remelted,  
softened, forging  
stock a or D  $\leq$  300 mm**

ICS 49.025.10

## National foreword

This British Standard is the UK implementation of EN 4346:2007.

The UK participation in its preparation was entrusted by Technical Committee ACE/61, Metallic materials for aerospace purposes, to Panel ACE/61/-/15, Steels.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

**Compliance with a British Standard cannot confer immunity from legal obligations.**

[www.parseethylene-kish.com](http://www.parseethylene-kish.com)

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2008

© BSI 2008

ISBN 978 0 580 59069 6

### Amendments/corrigenda issued since publication

Date	Comments

EUROPEAN STANDARD

EN 4346

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 2007

ICS 49.025.10

English Version

**Aerospace series - Steel FE-PM1505 (X1CrNiMoAlTi12-9-2) -  
Vacuum induction melted and consumable electrode remelted,  
softended, forging stock a or D ≤ 300 mm**

Série aérospatiale - Acier FE-PM1505 (X1CrNiMoAlTi12-9-2) - Elaboré sous vide par induction et refondu à l'électrode consommable, adouci, produits destinés à la forge a ou D ≤ 300 mm

Luft- und Raumfahrt - Stahl FE-PM1505 (X1CrNiMoAlTi12-9-2) - Vakuuminduktionserschmolzen und mit selbstverzehrender Elektrode umgeschmolzen, weichgeglüht, Schmiedevormaterial a oder D ≤ 300 mm

This European Standard was approved by CEN on 15 March 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

## **Contents**

Page

Foreword.....	3
Introduction .....	4
1 <b>Scope</b> .....	4
2 <b>Normative references</b> .....	4

[www.parsethylene-kish.com](http://www.parsethylene-kish.com)

## Foreword

This document (EN 4346:2007) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2008, and conflicting national standards shall be withdrawn at the latest by February 2008.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

www.parsethylene-kish.com

## Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

This standard has been prepared in accordance with EN 4500-5.

## 1 Scope

This standard specifies the requirements relating to:

Steel FE-PM1505 (X1CrNiMoAlTi12-9-2) — Vacuum induction melted and consumable electrode remelted, softened, forging stock  $a$  or  $D \leq 300$  mm

for aerospace applications.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2003-7, *Aerospace series — Steel, Test methods — Part 7: Macrographic test*<sup>1)</sup>

EN 2043, *Aerospace series — Metallic materials — General requirements for semi-finished product qualification (excluding forgings and castings)*<sup>1)</sup>

EN 2157-2, *Aerospace series — Steel — Forging stock and forgings — Technical specification — Part 2: Forging stock*

EN 4050-1, *Aerospace series — Test method for metallic materials — Ultrasonic inspection of bars, plates, forging stock and forgings — Part 1: General requirements*<sup>1)</sup>

EN 4258, *Aerospace series — Metallic materials — General organization of standardization — Links between types of EN standards and their use*

EN 4436, *Aerospace series — Steel — Test methods — Determination of  $\delta$  ferrite content*<sup>1)</sup>

EN 4500-5, *Aerospace series — Metallic materials — Rules for drafting and presentation of material standards — Part 5: Specific rules for steels*<sup>1)</sup>

---

<sup>1)</sup> Published as ASD prestandard at the date of publication of this standard.

<b>1</b>	<b>Material designation</b>		<b>Steel FE-PM1505 (X1CrNiMoAlTi12-9-2)</b>											
<b>2</b>	Chemical composition %	Element	C	Si	Mn	P	S	Cr	Mo	Ni	Al	N <sub>2</sub>	Ti	Fe
		min.	-	-	-	-	-	11,5	1,85	8,50	0,60	-	0,28	Base
		max.	0,015	0,10	0,10	0,010	0,005	12,5	2,15	9,50	0,80	0,010	0,37	
<b>3</b>	Method of melting		Vacuum induction melted and consumable electrode remelted											
<b>4.1</b>	Form		Forging stock											
<b>4.2</b>	Method of production		-											
<b>4.3</b>	Limit dimension(s)	mm	a or D ≤ 300											
<b>5</b>	Technical specification		EN 2157-2											

<b>6.1</b>	Delivery condition		Softened										
	Heat treatment		-										
<b>6.2</b>	Delivery condition code		U										
<b>7</b>	Use condition		Delivery condition										
	Heat treatment		-										

Characteristics

<b>8.1</b>	Test sample(s)		See EN 2157-2				Forged or machined			
<b>8.2</b>	Test piece(s)		See EN 2157-2				See EN 2157-2			
<b>8.3</b>	Heat treatment		Delivery condition				See line 29			
<b>9</b>	Dimensions concerned	mm	a or D ≤ 300				a or D < 75		75 ≤ a or D ≤ 300	
<b>10</b>	Thickness of cladding on each face	%	-				-		-	
<b>11</b>	Direction of test piece		-				L		T	
<b>12</b>	Temperature	$\theta$	°C		-				Ambient	
<b>13</b>	Proof stress	$R_{p0,2}$	MPa		-				≥ 1 300	
<b>14</b>	T Strength	$R_m$	MPa		-				≥ 1 400	
<b>15</b>	Elongation	A	%		-				≥ 9	
<b>16</b>	Reduction of area	Z	%		-				≥ 50	
<b>17</b>	Hardness		≤ 363 HB				≥ 400 HB		≥ 400 HB	
<b>18</b>	Shear strength	$R_c$	MPa		-				-	
<b>19</b>	Bending	k	-		-				-	
<b>20</b>	Impact strength		-				KV ≥ 40 J; Notch direction T		KV ≥ 30 J; Notch direction L	
<b>21</b>	Temperature	$\theta$	°C		-				-	
<b>22</b>	Time		h		-				-	
<b>23</b>	Stress	$\sigma_a$	MPa		-				-	
<b>24</b>	C Elongation	a	%		-				-	
<b>25</b>	Rupture stress	$\sigma_R$	MPa		-				-	
<b>26</b>	Elongation at rupture	A	%		-				-	
<b>27</b>	Notes (see line 98)		-				-			

29	Reference heat treatment	–	Solution treated and precipitation treated $820\text{ °C} \leq \theta \leq 860\text{ °C}$ / OQ, AQ or WQ + Cooling to $\theta \leq 20\text{ °C}$ + $510\text{ °C} \leq \theta \leq 530\text{ °C}$ / $t \geq 4\text{ h}$ / AC		
30	Microstructure	1	See EN 4436		
		2	One per cast		
		3	Corresponding to ingot top		
		5	See line 29		
		7	The $\delta$ -ferrite content shall not exceed 2 %		
44	External defects	–	See EN 2157-2		
50	Cleanliness/inclusion content (micro-cleanness)	–	See EN 2157-2		
		7	Category 5		
51	Macrostructure	1	EN 2003-7		
		7	Class	Condition	Severity
			1	Freckles	A
			2	White spots	A
			3	Radial segregation	A
4	Ring pattern	B			
61	Internal defects	–	See EN 2157-2		
		1	See EN 4050-1		
		7	Class 5		
95	Marking inspection	–	See EN 2157-2		
96	Dimensional inspection	–	See EN 2157-2		
98	Notes	–	–		
99	Typical use	–	–		



100	-	Product qualification	-	See EN 2043
				Qualification programme to be agreed between manufacturer and purchaser.

www.parsethylene-kish.com

## British Standards Institution (BSI)

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.

Tel: +44 (0)20 8996 9000 Fax: +44 (0)20 8996 7400

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services.

Tel: +44 (0)20 8996 9001 Fax: +44 (0)20 8996 7001

Email: [orders@bsigroup.com](mailto:orders@bsigroup.com)

You may also buy directly using a debit/credit card from the BSI Shop on the Website <http://www.bsigroup.com/shop>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.

Tel: +44 (0)20 8996 7111 Fax: +44 (0)20 8996 7048

Email: [info@bsigroup.com](mailto:info@bsigroup.com)

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.

Tel: +44 (0)20 8996 7002 Fax: +44 (0)20 8996 7001

Email: [membership@bsigroup.com](mailto:membership@bsigroup.com)

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsigroup.com/BSOL>.

Further information about BSI is available on the BSI website at <http://www.bsigroup.com>.

### Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.

Tel: +44 (0)20 8996 7070 Email: [copyright@bsigroup.com](mailto:copyright@bsigroup.com)