

DIN EN ISO 12162



ICS 83.080.01

Supersedes
DIN EN ISO 12162:1996-04

**Thermoplastics materials for pipes and fittings for pressure applications –
Classification, designation and design coefficient (ISO 12162:2009)
English translation of DIN EN ISO 12162:2010-04**

Thermoplastische Werkstoffe für Rohre und Formstücke für Anwendungen unter Druck –
Klassifizierung, Werkstoffkennzeichnung und Gesamtbetriebs-(berechnungs-)Koeffizient
(ISO 12162:2009)

Englische Übersetzung von DIN EN ISO 12162:2010-04

Matières thermoplastiques pour tubes et raccords pour applications avec pression –
Classification, désignation et coefficient de calcul (ISO 12162:2009)

Traduction anglaise de DIN EN ISO 12162:2010-04

Document comprises 14 pages

Translation by DIN-Sprachendienst.

In case of doubt, the German-language original shall be considered authoritative.

A comma is used as the decimal marker.

National foreword

This standard has been prepared by Technical Committee ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids" in collaboration with Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems" (Secretariat: NEN, Netherlands).

The responsible German body involved in its preparation was the *Normenausschuss Kunststoffe* (Plastics Standards Committee), Working Committee NA 054-05-02 AA *Prüfverfahren für Rohre*.

The DIN Standards corresponding to the International Standards referred to in this document are as follows:

ISO 1043-1	DIN EN ISO 1043-1
ISO 9080	DIN EN ISO 9080

Amendments

This standard differs from DIN EN ISO 12162:1996-04 as follows:

- a) The standard has been editorially and technically revised.
- b) In addition to the MRS classification, the CSR value has been specified as categorized required strength at a temperature θ and a time t .
- c) For new materials, the minimum design coefficient C_{\min} has been introduced.

Previous editions

DIN EN ISO 12162: 1995-11, 1996-04

National Annex NA (informative)

Bibliography

DIN EN ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics*

DIN EN ISO 9080, *Plastics piping and ducting systems — Determination of the long-term hydrostatic strength of thermoplastics materials in pipe form by extrapolation*

English Version

Thermoplastics materials for pipes and fittings for pressure applications — Classification, designation and design coefficient (ISO 12162:2009)

Matières thermoplastiques pour tubes et raccords pour applications avec pression — Classification, désignation et coefficient de calcul (ISO 12162:2009)

Thermoplastische Werkstoffe für Rohre und Formstücke für Anwendungen unter Druck — Klassifizierung, Werkstoffkennzeichnung und Gesamtbetriebs-(berechnungs-)Koeffizient (ISO 12162:2009)

This European Standard was approved by CEN on 10 October 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 MRS classification of materials in pipe form	7
5 $CRS_{\theta, t}$ value for specific design purposes	8
6 Design coefficient.....	8
7 Calculation of design stress based on MRS classification	9
8 Designation of materials in pipe form	9
Annex A (normative) The $CRS_{\theta, t}$ value.....	10
A.1 The $CRS_{\theta, t}$ value.....	10
A.2 Calculation of the design stress based on $CRS_{\theta, t}$ value.....	11
Bibliography.....	12

Foreword

This document (EN ISO 12162:2009) has been prepared by Technical Committee ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids" in collaboration with Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems" the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2010, and conflicting national standards shall be withdrawn at the latest by May 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 12162:1995.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 12162:2009 has been approved by CEN as a EN ISO 12162:2009 without any modification.

Introduction

The revision of this International Standard incorporates the introduction of a $CRS_{\theta,t}$ value (categorized required strength at a temperature θ and time t), in addition to the MRS classification and the introduction of minimum design coefficients for additional materials.

The classification in this International Standard does not qualify a material for a specific application. For specific applications, the relevant product standards require that additional mechanical and physical properties be met.

www.parsethylene-kish.com

1 Scope

This International Standard establishes the classification of thermoplastics materials in pipe form and specifies the material designation. It also specifies a method for calculating the design stress.

It is applicable to materials intended for pipes and fittings for pressure applications.

NOTE 1 Classification, minimum design coefficient and calculation method are based on the resistance to internal pressure with water at 20 °C for 50 years, derived by extrapolation using the method given in ISO 9080.

NOTE 2 Design coefficients for multilayer pipes are described in the appropriate product (system) standards.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics*

ISO 9080, *Plastics piping and ducting systems — Determination of the long-term hydrostatic strength of thermoplastics materials in pipe form by extrapolation*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

long-term hydrostatic strength

σ_{LTHS}

quantity, with the dimension of stress, which represents the predicted mean strength at a temperature θ and time t

NOTE 1 The quantity is expressed in megapascals.

NOTE 2 Temperature, θ , is expressed in degrees Celsius and time, t , is expressed in years.

3.2

lower confidence limit of the predicted hydrostatic strength

σ_{LPL}

quantity, with the dimensions of stress, which represents the 97,5 % lower confidence limit of the predicted hydrostatic strength at a temperature θ and time t

NOTE 1 The quantity is expressed in megapascals.

NOTE 2 Temperature, θ , is expressed in degrees Celsius and time, t , is expressed in years.

3.3 minimum required strength

MRS

value of σ_{LPL} at 20 °C and 50 years, rounded down to the next smaller value of the R10 series or the R20 series

NOTE The R10 series conforms to ISO 3^[1] and the R20 series conforms to ISO 497^[2].

3.4 categorized required strength at temperature θ and time t

CRS _{θ, t}

value of σ_{LPL} at temperature θ and time t , rounded down to the next smaller value of the R10 series or the R20 series

NOTE 1 CRS _{θ, t} at 20 °C and 50 years equals MRS.

NOTE 2 Temperature, θ , is expressed in degrees Celsius and time, t , is expressed in years.

NOTE 3 The R10 series conforms to ISO 3^[1] and the R20 series conforms to ISO 497^[2].

3.5 design coefficient

C

coefficient with a value greater than 1, which takes into consideration service conditions as well as properties of the components of a piping system other than those represented in the lower confidence limit

NOTE 1 The minimum value of C , C_{min} , is defined and given for various thermoplastics pipe systems in Clause 6.

NOTE 2 The design coefficient for a given application is specified in the relevant product (system) standard.

3.6 Design stress

3.6.1 design stress based on MRS classification

σ_s

stress derived by dividing MRS by the design coefficient C , i.e. $\sigma_s = MRS/C$

NOTE 1 The maximum allowable design stress for a given material is derived by dividing MRS by the minimum design coefficient, C_{min} , i.e. $\sigma_s = MRS/C_{min}$.

NOTE 2 Design stress for a specific application is specified in the relevant product (system) standard.

3.6.2 design stress based on CRS _{θ, t} value

$\sigma_{s, \theta, t}$

stress derived by dividing CRS _{θ, t} by the design coefficient C , i.e. $\sigma_{s, \theta, t} = CRS_{\theta, t}/C$

NOTE 1 The maximum allowable design stress for a given material is derived by dividing CRS _{θ, t} by the minimum design coefficient, C_{min} , i.e. $\sigma_{s, \theta, t} = CRS_{\theta, t}/C_{min}$.

NOTE 2 Design stress for a specific application is specified in the relevant product (system) standard.

4 MRS classification of materials in pipe form

A thermoplastics material shall be classified by its σ_{LPL} values at 20 °C and 50 years, rounded down to the next smaller value of the R10 series for $\sigma_{LPL} < 10$ MPa or to the next smaller value of the R20 series for $\sigma_{LPL} \geq 10$ MPa. This constitutes the MRS.

The classification number for a thermoplastics material shall be 10 times the MRS (when expressed in megapascals) as indicated in Table 1.

Table 1 — MRS classification at 20 °C and 50 years

Range of lower confidence limits σ_{LPL} MPa	Minimum required strength MRS MPa	Classification number ^a
$1 \leq \sigma_{LPL} < 1,25$	1	10
$1,25 \leq \sigma_{LPL} < 1,6$	1,25	12.5
$1,6 \leq \sigma_{LPL} < 2$	1,6	16
$2 \leq \sigma_{LPL} < 2,5$	2	20
$2,5 \leq \sigma_{LPL} < 3,15$	2,5	25
$3,15 \leq \sigma_{LPL} < 4$	3,15	31.5
$4 \leq \sigma_{LPL} < 5$	4	40
$5 \leq \sigma_{LPL} < 6,3$	5	50
$6,3 \leq \sigma_{LPL} < 8$	6,3	63
$8 \leq \sigma_{LPL} < 10$	8	80
$10 \leq \sigma_{LPL} < 11,2$	10	100
$11,2 \leq \sigma_{LPL} < 12,5$	11,2	112
$12,5 \leq \sigma_{LPL} < 14$	12,5	125
$14 \leq \sigma_{LPL} < 16$	14	140
$16 \leq \sigma_{LPL} < 18$	16	160
$18 \leq \sigma_{LPL} < 20$	18	180
$20 \leq \sigma_{LPL} < 22,4$	20	200
$22,4 \leq \sigma_{LPL} < 25$	22,4	224
$25 \leq \sigma_{LPL} < 28$	25	250
$28 \leq \sigma_{LPL} < 31,5$	28	280
$31,5 \leq \sigma_{LPL} < 35,5$	31,5	315
$35,5 \leq \sigma_{LPL} < 40$	35,5	355
$40 \leq \sigma_{LPL} < 45$	40	400
$45 \leq \sigma_{LPL} < 50$	45	450
$50 \leq \sigma_{LPL} < 56$	50	500

^a If the classification number is not an integer, a full stop is used instead of a comma.

5 $CRS_{\theta, t}$ value for specific design purposes

For design purposes at times other than 50 years and constant temperatures other than 20 °C, materials may be further described by a $CRS_{\theta, t}$ value. These values are not intended for use in applications with temperature profiles, e.g. as defined in ISO 10508^[3] for hot and cold water installations.

$CRS_{\theta, t}$ is determined from the value of σ_{LPL} at a temperature θ and a time t , by rounding it down to the next smaller value of the R10 series for $\sigma_{LPL} < 10$ MPa or by rounding down to the next smaller value of the R20 series for $\sigma_{LPL} \geq 10$ MPa. This constitutes the $CRS_{\theta, t}$ value as indicated in Annex A.

6 Design coefficient

The values of the design coefficient, C , are specified in the relevant product standards.

The values of the minimum design coefficient, C_{min} , at 20 °C for thermoplastics piping systems shall be equal to the value given in Table 2.

Higher design coefficients may be chosen in the case of:

- a) specific requirements for the products, such as additional stresses and other effects which are considered to occur in the application;
- b) influence of temperature and time (if different from 20 °C, 50 years) and/or influence of environment;
- c) standards that are based on MRS, where other temperatures of operation are required.

Table 2 — Values of C_{min}

Thermoplastics piping system	C_{min}
ABS	1,6
PB	1,25
PE (all types)	1,25
PE-X	1,25
PP copolymer	1,25
PP homopolymer	1,6
PVC-C	1,6
PVC-HI	1,4
PVC-U	1,6
PVC-O (for MRS ≤ 40)	1,6 ^a
PVC-O (for MRS > 40)	1,4 ^a
PVDF copolymer	1,4
PVDF homopolymer	1,6
PA11	1,6
PA12	1,6
PPSU	1,4
^a In accordance with Table 1 of ISO 16422:2006 ^[4]	

7 Calculation of design stress based on MRS classification

The design stress, σ_s , shall be calculated using Equation (1) and rounded to the next lower value in the R20 series:

$$\sigma_s = \frac{MRS}{C} \quad (1)$$

where

MRS is the value of the minimum required strength (see 3.3);

C is the applicable value of design coefficient in accordance with Clause 6.

Unless otherwise specified in the relevant product standards, the maximum allowable design stress shall be calculated using the minimum design coefficient, C_{min} .

8 Designation of materials in pipe form

The designation of materials in pipe form shall include the following:

- the symbol of the material in accordance with ISO 1043-1;
- its classification number in accordance with Clause 4, unless otherwise specified in the product standards.

Example of the MRS designation of a PVC-U, with an MRS value of 25 MPa:

PVC-U 250

A material may be designated to the next lower classification number.

Annex A (normative)

The $CRS_{\theta, t}$ value

A.1 The $CRS_{\theta, t}$ value

The $CRS_{\theta, t}$ values are given in Table A.1.

The selected $CRS_{\theta, t}$ time, t , shall not exceed 100 years. The extrapolation time factors stated in ISO 9080 shall be respected. The selected $CRS_{\theta, t}$ temperature, θ , shall neither exceed the maximum ISO 9080 test temperature for the material in question, nor be more than 20 °C below the lowest ISO 9080 test temperature, provided that the material is still suitable for the intended application.

Table A.1 — $CRS_{\theta, t}$ values

Range of lower confidence limits σ_{LPL} MPa	Categorized required strength $CRS_{\theta, t}$ MPa
$1 \leq \sigma_{LPL} < 1,25$ $1,25 \leq \sigma_{LPL} < 1,6$ $1,6 \leq \sigma_{LPL} < 2$ $2 \leq \sigma_{LPL} < 2,5$ $2,5 \leq \sigma_{LPL} < 3,15$	1 1,25 1,6 2 2,5
$3,15 \leq \sigma_{LPL} < 4$ $4 \leq \sigma_{LPL} < 5$ $5 \leq \sigma_{LPL} < 6,3$ $6,3 \leq \sigma_{LPL} < 8$ $8 \leq \sigma_{LPL} < 10$	3,15 4 5 6,3 8
$10 \leq \sigma_{LPL} < 11,2$ $11,2 \leq \sigma_{LPL} < 12,5$ $12,5 \leq \sigma_{LPL} < 14$ $14 \leq \sigma_{LPL} < 16$ $16 \leq \sigma_{LPL} < 18$	10 11,2 12,5 14 16
$18 \leq \sigma_{LPL} < 20$ $20 \leq \sigma_{LPL} < 22,4$ $22,4 \leq \sigma_{LPL} < 25$ $25 \leq \sigma_{LPL} < 28$ $28 \leq \sigma_{LPL} < 31,5$	18 20 22,4 25 28
$31,5 \leq \sigma_{LPL} < 35,5$ $35,5 \leq \sigma_{LPL} < 40$ $40 \leq \sigma_{LPL} < 45$ $45 \leq \sigma_{LPL} < 50$ $50 \leq \sigma_{LPL} < 56$	31,5 35,5 40 45 50

As an example of the use of the $CRS_{\theta, t}$ value, material with $\sigma_{LPL} = 6,4$ MPa at a given temperature of 70 °C and time of 20 years is described as follows:

EXAMPLE $CRS_{70^{\circ}C, 20 \text{ years}} = 6,3$ MPa

A.2 Calculation of the design stress based on $CRS_{\theta, t}$ value

The design stress, $\sigma_{s, \theta, t}$, shall be calculated using Equation (A.1):

$$\sigma_{s, \theta, t} = \frac{CRS_{\theta, t}}{C} \quad (A.1)$$

where

$CRS_{\theta, t}$ is the value of the categorized required strength (see 3.4);

C is the applicable value of design coefficient in accordance with Clause 6.

Unless otherwise specified in the relevant product (system) standards, the maximum allowable design stress shall be calculated using C_{min} .

Bibliography

- [1] ISO 3, *Preferred numbers — Series of preferred numbers*
- [2] ISO 497, *Guide to the choice of series of preferred numbers and of series containing more rounded values of preferred numbers*
- [3] ISO 10508, *Plastics piping systems for hot and cold water installations — Guidance for classification and design*
- [4] ISO 16422:2006, *Pipes and joints made of oriented unplasticized poly(vinyl chloride) (PVC-O) for the conveyance of water under pressure — Specifications*

www.parsethylene-kish.com